

IN THE CLAIMS

Please cancel claims 4 and 11 without prejudice.

Please amend claims 1-3, 5-10, 12 and 13 as shown in the attached marked-up copy to read as follows.

1. (Amended) A method for manufacturing a semiconductor device comprising:
- forming a dummy gate electrode on a semiconductor substrate having a predetermined length coincident with a length of a gate electrode to be formed;
- with the dummy gate electrode used as a mask, forming one pair of first impurity diffusion layers in regions of the semiconductor substrate which are opposite to each other on opposite sides of the dummy gate electrode;
- forming an insulating film on the semiconductor substrate so as to bury the dummy gate electrode and exposing an upper surface of the dummy gate electrode;
- removing the dummy gate electrode to form a first trench electrode in the insulating film having a width corresponding to at least the predetermined length of the dummy gate;
- enlarging the width of the first trench on each side of the first trench by a predetermined amount to form a second trench in the insulating film, said predetermined amount being equal to or greater than a thickness of a gate insulation film to be lined on an inner surface of the second trench;
- lining the gate insulating film of said thickness along the inner surface of the second trench; and
- forming the gate electrode in the second trench with only the gate insulating film intervening therebetween.
2. (Amended) The method according to claim 1, further comprising:

after forming the first impurity diffusion layers, forming a side wall insulating film on a side wall surface of the dummy gate electrode; and

with the dummy gate electrode and the sidewall insulating film used as a mask, forming second impurity diffusion layers having a deeper junction in the semiconductor substrate than the first impurity diffusion layers.

3. (Amended) The method according to claim 1, wherein the forming of a second trench includes performing an isotropic etching on the insulating film having the first trench formed therein.

5. (Amended) The method according to claim 1, wherein the forming of a gate insulating film includes using an insulating material having a relative dielectric constant of above 5.

6. (Amended) The method according to claim 1, wherein the forming of a gate insulating film includes using an insulating material selected from the group consisting of Ta₂O₅, silicon nitride, Al₂O₃, BaSrTiO₃, Zr oxide, Hf oxide, Sc oxide, Y oxide and Ti oxide.

7. (Amended) A method of manufacturing a semiconductor device, comprising:
forming a first insulating film on a semiconductor substrate;
sequentially forming a first semiconductor film and a second insulating film on the first insulating film;

forming a resist pattern on the second insulating film;

with the resist pattern used as a mask, patterning the first semiconductor film and the second insulating film by an anisotropic etching to provide a stacked layer structure of the first semiconductor film and the second insulating film on the semiconductor substrate having a predetermined width coincident with a length of a gate electrode to be formed;

with the stacked layer structure used as a mask, ion-implanting an impurity in the semiconductor substrate to provide first impurity diffusion layers for a source and a drain; forming a third insulating film over the semiconductor structure to bury the stacked layer structure;

etching back the third insulating film to expose an upper surface of the stacked layer structure;

with the third insulating film used as a mask, removing the stacked layer structure to form a trench in the third insulating film;

after forming the trench, enlarging the width of the trench by an isotropic etching by a predetermined width amount on each side of the trench that is equal to or larger than a thickness of a fourth insulating film along an inner surface of the trench;

after enlarging the width of the trench, depositing the fourth insulating film of said thickness along the inner surface of the trench; and

forming a conductive layer on and in contact with the fourth insulating film to form said gate electrode of a length coincident with the predetermined width.

8. (Amended) The method according to claim 7, further comprising:

after providing the first impurity diffusion layers, forming a sidewall insulating film on a sidewall of the stacked layer structure; and

with the sidewall insulating film and the stacked layer structure used as a mask, forming second impurity diffusion layers having a deeper junction in the semiconductor substrate than the first impurity diffusion layers.

9. (Amended) The method according to claim 7, wherein the enlarging of the width of the trench includes using, as the isotropic etching, an etching treatment including HF or NH₄F.